



Technical Data: Q-Connect Premium

Basis weight	g/m²	ISO 536	80	± 3.0
Caliper	µm	ISO 534	103	± 3
Opacity	%	ISO 2471	92.0	± 1
Moisture abs.	%	ISO 287	4.6	± .6
Brightness UV	%	ISO 2470	110.5	± 1.5
CIE Whiteness	%	ISO 11475	161	± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and ISO 45001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

This specification is valid for one year after issue or good till cancelled.