


W50 – W59




W50




W51




W52




W53




W54




W55




W56



W57



W58



W59

W50 – W59



DEUTSCH

Zusammensetzung 100 % Polyester
Gewicht 560g / Laufmeter
Lichtechtheit Note 5-7 (EN ISO 105 B02)
Reibechtheit Note 4-5 trocken und nass (EN ISO 105X12)
Scheuerfestigkeit 50.000 Touren Martindale (EN ISO 12947)
Feuersicherung DIN EN 1021 Teil 1 DIN EN 1021 Teil 2

ENGLISH

Composition 100 % Polyester
Weight 560g / linear metre
Lightfastness grade 5-7 (EN ISO 105 B02)
Rubfastness grade 4-5 dry and wet (EN ISO 105X12)
Abrasion resistance 50.000 cycles Martindale (EN ISO 12947)
Fire resistance DIN EN 1021 part 1 DIN EN 1021 part 2

FRANÇAIS

Composition 100 % Polyester
Poids 560g / mètre linéaire
Résistance à la lumière note 5-7 (EN ISO 105 B02)
Résistance au frottement note 4-5 sec et mouillé (EN ISO 105X12)
Résistance à l'abrasion 50.000 tours Martindale (EN ISO 12947)
Inflammabilité DIN EN 1021 partie 1 DIN EN 1021 partie 2

ITALIANO

Composizione 100 % Poliestere
Peso 560g / metro lineare
Resistenza alla luce voto 5-7 (EN ISO 105 B02)
Solidità allo sfregamento voto 4-5 bagnato e asciutto (EN ISO 105X12)
Resistenza all'abrasione 50.000 cicli Martindale (EN ISO 12947)
Inflammabilità DIN EN 1021 parte 1 DIN EN 1021 parte 2